

In re Patent Application of:
MAGRI' ET AL.
Serial No. 10/749,134
Filing Date: DECEMBER 30, 2003

In the Claims:

This listing of claims replaces all prior versions and listing of claims in the application.

Claims 1-23 (Cancelled).

24. (Currently Amended) A method for forming a semiconductor device ~~vertical conduction and planar structure MOS device having a double thickness gate oxide,~~ the method comprising:

forming spaced apart active areas in a semiconductor substrate and defining a JFET area therebetween, the JFET area also forming a channel between the spaced apart active areas; and

forming a gate oxide on the semiconductor substrate and comprising a first portion having a first thickness on the active areas and at a periphery of the JFET area, and a second portion having a second thickness on a central area of the JFET area, the second thickness being greater than the first thickness, wherein forming the gate oxide comprises

~~forming a first portion having a first thickness on the active areas and at a periphery of the JFET area, and~~

~~forming a second portion having a second thickness on a central area of the JFET area, the second thickness being greater than the first thickness; and~~

~~forming an enrichment region in the JFET area under the second portion of the gate oxide.~~

In re Patent Application of:
MAGRI' ET AL.
Serial No. 10/749,134
Filing Date: DECEMBER 30, 2003

forming an oxide pad on the active areas and on the channel,
forming a nitride layer on the oxide pad,
forming a photoresist layer on the nitride layer except over a portion of the JFET area corresponding to the second portion of the gate oxide,
removing the exposed nitride layer,
implanting dopants through the exposed oxide pad while using the photoresist as an implant window for forming an enrichment region in the JFET area under the second portion of the gate oxide, and
removing the photoresist layer.

25. (Previously Presented) A method according to Claim 24, wherein the enrichment region is self-aligned with the second portion of the gate oxide.

26. (Previously Presented) A method according to Claim 24, wherein an interface between the first and second portions of the gate oxide has a tapered thickness.

27. (Canceled).

28. (Currently Amended) A method according to ~~Claim 27~~ Claim 24, wherein forming the gate oxide comprises:
growing the oxide pad for forming the first portion of the gate oxide layer;
removing the nitride layer;
selectively removing the first portion of the gate

In re Patent Application of:
MAGRI' ET AL.
Serial No. 10/749,134
Filing Date: **DECEMBER 30, 2003**

oxide layer on a central area of the active areas;
forming a sacrificial oxide layer on the first
portion of the gate oxide layer;
removing the sacrificial oxide layer to expose a
gate region on the channel; and
growing the first portion of the gate oxide layer on
the gate region for forming the second portion of the gate
oxide.

29. (Currently Amended) A method according to ~~Claim-
27, Claim 24,~~ wherein the oxide pad has a thickness within a
range of about 100 to 500 Å; and wherein the nitride layer has
a thickness with a range of about 300 to 900 Å.

30. (Currently Amended) A method according to ~~Claim-
27, Claim 24,~~ wherein the dopants comprise at least one of P,
As and Sb ions for an N-channel transistor, and with the
implanting being performed at an implant energy within a range
of 60 to 900 KeV with ion doses ranging between $1E12$ to $1E13$
ions/cm².

31. (Currently Amended) A method according to ~~Claim-
27, Claim 24,~~ wherein the dopants comprise at least one of B
and Al ions for a P-channel transistor, and with the
implanting being performed at an implant energy within a range
of 60 to 900 KeV with ion doses ranging between $1E12$ to $1E13$
ions/cm².

Claims 32-37 (Cancelled).

In re Patent Application of:
MAGRI' ET AL.
Serial No. 10/749,134
Filing Date: DECEMBER 30, 2003

38. (Currently Amended) A method for forming a semiconductor device comprising:

forming spaced apart ~~source and drain~~ active areas
in a semiconductor substrate and defining a JFET area
therebetween, the JFET area also forming a channel between the
source and drain areas;

forming a gate oxide on the semiconductor substrate
and comprising a first portion having a first thickness on the
active areas and at a periphery of the JFET area, and a second
portion having a second thickness on a central area of the
JFET area, the second thickness being greater than the first
thickness, wherein forming the gate oxide comprises

~~forming a first portion having a first~~
~~thickness on the source and drain areas and at a~~
~~periphery of the JFET area,~~

~~forming a second portion having a second~~
~~thickness on a central area of the JFET area, the second~~
~~thickness being greater than the first thickness, and~~

~~forming an enrichment region in the JFET area~~
~~under the second portion of the gate oxide.~~

forming an oxide pad on the active areas and on
the channel,

forming a polysilicon layer having a thickness
less than or equal to one-half the second thickness of
the second portion of the gate oxide,

forming a nitride layer on the polysilicon
layer,

In re Patent Application of:
MAGRI' ET AL.
Serial No. 10/749,134
Filing Date: DECEMBER 30, 2003

forming a photoresist layer on the nitride layer except over a portion of the JFET area corresponding to the second portion of the gate oxide,
removing the exposed nitride layer,
implanting dopants through the exposed polysilicon layer while using the photoresist layer as an implant window for forming the enrichment region in the JFET area,
removing the photoresist layer,
oxidizing the polysilicon layer not covered by the nitride layer, and
removing the nitride layer; and
forming a gate electrode on the first and second portions of the gate oxide.

39. (Canceled).

40. (Previously Presented) A method according to Claim 38, wherein the enrichment region is self-aligned with the second portion of the gate oxide.

41. (Previously Presented) A method according to Claim 38, wherein an interface between the first and second portions of the gate oxide has a tapered thickness.

Claims 42-47 (Cancelled).

48. (Currently Amended) A method according to ~~Claim 47,~~ Claim 38, wherein the oxide pad has a thickness within a

In re Patent Application of:
MAGRI' ET AL.
Serial No. 10/749,134
Filing Date: **DECEMBER 30, 2003**

range of about 100 to 1500 Å; and wherein the nitride layer has a thickness with a range of about 300 to 900 Å.

49. (Currently Amended) A method according to ~~Claim 47~~, Claim 38, wherein the dopants comprise at least one of P, As and Sb ions for an N-channel transistor, and with the implanting being performed at an implant energy within a range of 60 to 900 KeV with ion doses ranging between $1E12$ to $1E13$ ions/cm².

50. (Currently Amended) A method according to ~~Claim 47~~, Claim 38, wherein the dopants comprise at least one of B and Al ions for a P-channel transistor, and with the implanting being performed at an implant energy within a range of 60 to 900 KeV with ion doses ranging between $1E12$ to $1E13$ ions/cm².